

WHAT IS CLAIMED IS:

1. A semiconductor device, comprising:

sub
A1

a capacitor provided on a supporting substrate having an integrated circuit thereon and including a lower electrode, a dielectric film, and an upper electrode;

a first interlayer insulating film provided so as to cover the capacitor;

a first interconnect selectively provided on the first interlayer insulating film and electrically connected to the integrated circuit and the capacitor through a first contact hole formed in the first interlayer insulating film;

a second interlayer insulating film formed of ozone TEOS and provided so as to cover the first interconnect;

a second interconnect selectively provided on the second interlayer insulating film and electrically connected to the first interconnect through a second contact hole formed in the second interlayer insulating film; and

a passivation layer provided so as to cover the second interconnect.

2. A semiconductor device according to claim 1, wherein the dielectric film is formed from either a dielectric material having a high dielectric constant or a ferroelectric material.

3. A semiconductor device according to claim 1, wherein the second interconnect is provided on the second interlayer insulating film so as to cover at least a part of

~~the capacitor.~~

4. A semiconductor device according to claim 1, wherein the passivation layer is formed from a laminate including a silicon oxide film and a silicon nitride film.

5. A semiconductor device according to claim 1, further comprising a hydrogen supplying layer provided between the first interconnect and the second interlayer insulating film excluding an area in which the capacitor is provided.

6. A semiconductor device according to claim 1, wherein the first interconnect is formed from a laminate including titanium, titanium nitride, aluminum and titanium nitride; a laminate including titanium, titanium nitride and aluminum; a laminate including titanium, titanium tungsten, aluminum and titanium tungsten; or a laminate including titanium, titanium tungsten and aluminum.

7. A semiconductor device according to claim 1, wherein a Si-OH bond absorption coefficient of the second interlayer insulating film at a wavelength corresponding to 3450 cm^{-1} is 800 cm^{-1} or less.

8. A semiconductor device according to claim 1, wherein the second interlayer insulating film has a tensile stress of $1 \times 10^7\text{ dyn/cm}^2$ to $3 \times 10^9\text{ dyn/cm}^2$ inclusive.

9. A semiconductor device according to claim 1, wherein the second interlayer insulating film has a thickness of $0.3\text{ }\mu\text{m}$ to $1\text{ }\mu\text{m}$ inclusive.

10. A semiconductor device according to claim 1, wherein the second interconnect is formed from a laminate including titanium, aluminum and titanium nitride; a laminate including titanium and aluminum; or a laminate including titanium, aluminum and titanium tungsten.

11. A method for fabricating a semiconductor device, comprising the steps of:

sequentially forming a lower electrode, a dielectric film, and an upper electrode on a supporting substrate having an integrated circuit, thereby forming a capacitor;

forming a first interlayer insulating film so as to cover the capacitor;

forming a first contact hole in the first interlayer insulating film;

selectively forming a first interconnect in the first contact hole and on a prescribed area of the first interlayer insulating film so as to be electrically connected to the integrated circuit and the capacitor;

forming a second interlayer insulating film of ozone TEOS so as to cover the first interconnect;

subjecting the second interconnect to a first thermal treatment;

forming a second contact hole in the second interlayer insulating film;

selectively forming a second interconnect in the second contact hole and on a prescribed area of the second interlayer insulating film so as to be electrically connected to the first interconnect;

subjecting the second interconnect to a second thermal treatment; and

forming a passivation layer so as to cover the

second interconnect.

12. A method for fabricating a semiconductor device according to claim 11, wherein the dielectric film is formed from either a dielectric material having a high dielectric constant or a ferroelectric material.

13. A method for fabricating a semiconductor device according to claim 11, further comprising the step of etching back the second interlayer insulating film using the second interconnect as a mask to such an extent as to almost expose the first interconnect.

14. A method for fabricating a semiconductor device according to claim 11, wherein the step of forming the second interconnect includes the step of forming the second interconnect so as to cover at least a part of the capacitor.

15. A method for fabricating a semiconductor device according to claim 11, wherein:

the passivation layer is formed of a laminate including a silicon oxide film and a silicon nitride film, and

the silicon oxide film is formed by normal-pressure CVD, low-pressure CVD or plasma CVD, with using silane, disilane or ozone TEOS, so as to have a tensile stress.

16. A method for fabricating a semiconductor device according to claim 11, further comprising the steps of:

after the first interconnect is formed, forming a hydrogen supplying layer on the first interconnect

excluding an area where the capacitor is provided; and performing a third thermal treatment.

17. A method for fabricating a semiconductor device according to claim 16, wherein the hydrogen supplying layer is formed from either silicon nitride or silicon nitride oxide by plasma CVD.

18. A method for fabricating a semiconductor device according to claim 16, wherein the third treatment performed after the formation of hydrogen supplying layer is performed at a temperature in the range of 300°C to 450°C inclusive.

19. A method for fabricating a semiconductor device according to claim 16, wherein the third treatment performed after the formation of the hydrogen supplying layer is performed in an oxygen atmosphere, a nitrogen atmosphere, an argon atmosphere or an atmosphere of a mixed gas thereof.

20. A method for fabricating a semiconductor device according to claim 11, wherein the first interlayer insulating film is formed of silicon oxide by normal-pressure CVD or low-pressure CVD, with using silane, disilane or ozone TEOS.

21. A method for fabricating a semiconductor device according to claim 11, wherein the first interlayer insulating film is formed of phosphorus-doped silicon oxide by normal-pressure CVD or low-pressure CVD.

22. A method for fabricating a semiconductor device according to claim 11, wherein an ozone concentration upon forming the second interlayer insulating film using ozone TEOS is set to be at 5.5% or more.

23. A method for fabricating a semiconductor device according to claim 11, wherein the second interlayer insulating film after being subjected with the first thermal treatment has a tensile stress of 1×10^7 dyn/cm² to 2×10^9 dyn/cm² inclusive.

24. A method for fabricating a semiconductor device according to claim 11, wherein the first thermal treatment is performed at a temperature in the range of 300°C to 450°C inclusive.

25. A method for fabricating a semiconductor device according to claim 11, wherein the first thermal treatment is performed in an atmosphere containing at least oxygen.

26. A method for fabricating a semiconductor device according to claim 11, wherein the second thermal treatment is performed at a temperature in the range of 300°C to 450°C inclusive.

27. A method for fabricating a semiconductor device according to claim 11, wherein the second thermal treatment is performed in an atmosphere containing at least one of nitrogen, argon and helium.

add
A2

add
B1

add C3

add D3